



## SYNAUGUSTINE 347

Our softest, most realistic, most comfortable variety of grass with beautiful multi-colored grass blades incorporating Super Yarn Technology. This grass takes the lead in comfort, strength, and realistic natural turf aesthetics.

SKU	SA347
Grass Zone Yarn/Color	PE / Field Green / Olive / Apple
Grass Zone Denier	9,900 / 9
Thatch Zone Yarn/Color	PE / Field Green / Beige
Thatch Zone Denier	5,000 / 8
Grass Zone Yarn Shape	Soft Omega
Finished Pile Height	1 7/8"
Finished Pile Weight	75 oz.
Backing	13PP/18PET 2pt / 22oz. EnviroLoc+™
Tuft Gauge	3/8"
Total Weight	103 oz.
Tuf Bind	> 8 lbs.
Permeability	> 800 inches p/hr
Features	Sanitized®, EnviroLoc+™, StatBlock™ Anti-Static, DualChill™ IR Reflective, Deluster, UV Stabilizers
Test Data	USDA SYSTEM, ASTM E108 CLASS A, ASTM D2859, E648, F1292, F1951, IPEMA, PFA-FREE



### SUPER YARN™ TECHNOLOGY

**SANITIZED®**  
ANTIMICROBIAL

**DUALCHILL™**  
IR REFLECTIVE

**STATBLOCK™**  
ANTI-STATIC



UNMATCHED LIFETIME WARRANTY



OPTIMAL DRAINAGE >800" P/H




USE IN ALL CLIMATES AND REGIONS



SAFE FOR CHILDREN AND PETS

ASK ABOUT OUR...  
**USDA CERTIFIED  
ORGANIC INFILL  
SYSTEM**



**USDA  
CERTIFIED  
BIOBASED  
PRODUCT**  
PRODUCT 71%

SYNAugustine 347 is a USDA Certified Bio-Based artificial grass system in combination with organic infill, able to display a unique USDA label highlighting its percentage of biobased content.



Primary Yarn Polymer	Polyethylene	Primary Backing	13PP/18PET 2pt
Yarn Cross Section	Soft Omega	Coating Type	22 oz. EnviroLoc+
Standard Color	Field Green / Olive / Apple	PE Yarn Denier / Ends	9,900 / 9
Fabric Construction	Tufted	Texturized Thatch Denier / Ends	5,000 / 8
Second Yarn Polymer Thatch	Polyethylene	Warranty Period	Limited Lifetime
Secondary Yarn Color	Field Green / Beige		

FINISH FABRIC	ENGLISH SYSTEM		ASTM TEST
	Nominal Specification	Value	Units
Pile Height (Nominal)	1 7/8	inches	D-5823
Face Weight	75	oz/yd <sup>2</sup>	D-5848
Total Fabric Weight	103	oz/yd <sup>2</sup>	D-5848
Primary Backing Weight	6	oz/yd <sup>2</sup>	D-5848
Secondary Coating Weight	22	oz/yd <sup>2</sup>	D-5848
Tuft Bind	> 8	lbs.	D-1335
Grab Tear Strength (Average)	> 200	lbs.	D-5034
Total Yarn Linear Density	14,900	Denier	D-1577
Elongation to Break	> 30	%	D-2256
Yarn Breaking Strength	> 20	lbs.	D-5793
Machine Gauge	3/8	inches	D-5793
Flammability	Passed	-	D-2859
Water Permeability	>800	in/hr	D-1551
Fabric Width	15	ft	-