



COMING SOON

SYNRYE 239

Experience unrivaled safety and performance with this synthetic grass designed for high-traffic foot areas like office buildings and schools. Boasting an ASTM CERTIFIED E108 CLASS A FIRE-RATING, it offers top-notch fire safety, ideal for demanding environments.

| | |
|------------------------|--|
| SKU | SR239 |
| Grass Zone Yarn/Color | Nylon / Field Green/Olive |
| Grass Zone Denier | 6,000 / 8 |
| Thatch Zone Yarn/Color | Nylon / Field Green/Tan |
| Thatch Zone Denier | 4,000 / 8 |
| Grass Zone Yarn Shape | Textured |
| Finished Pile Height | 1 3/8" |
| Finished Pile Weight | 60 oz. |
| Backing | (2) 13 pic PP / 22oz. EnviroLoc+™ |
| Tuft Gauge | 3/8" |
| Total Weight | 88 oz. |
| Tuft Bind | > 8 lbs. |
| Permeability | > 250 inches p/hr |
| Features | EnviroLoc+™ |
| Test Data | ASTM E108 CLASS A FIRE, D2859, E648, EN12616 |



ASTM E108 CLASS A FIRE RATING



LIMITED LIFETIME WARRANTY*



UV PROTECTED FROM REFLECTING LIGHT



FOR HIGH-TRAFFIC ROOFTOPS AND COMMERCIAL APPLICATIONS

INSTALLATION DETAILS AVAILABLE AT



CADdetails

MasterSpec®

NOT TO SCALE. FOR ILLUSTRATION ONLY. CONTACT YOUR LOCAL SYNLAWN FOR INSTALLATION.



ROOF



MULTI-USE



PLAY



LANDSCAPE



GOLF



| | | | |
|----------------------------|-------------------|---------------------------------|-------------------|
| Primary Yarn Polymer | Nylon | Primary Backing | (2) 13 pic PP |
| Yarn Cross Section | Texturized | Coating Type | 22 oz. EnviroLoc+ |
| Standard Color | Field Green/Olive | PE Yarn Denier / Ends | 6,000 / 8 |
| Fabric Construction | Tufted | Texturized Thatch Denier / Ends | 4,000 / 8 |
| Second Yarn Polymer Thatch | Nylon | Warranty Period | Limited Lifetime |
| Secondary Yarn Color | Field Green/Tan | | |

| FINISH FABRIC | ENGLISH SYSTEM | | ASTM TEST |
|------------------------------|-----------------------|--------------------|-----------|
| | Nominal Specification | Value | Units |
| Pile Height (Nominal) | 1 3/8 | inches | D-5823 |
| Face Weight | 60 | oz/yd ² | D-5848 |
| Total Fabric Weight | 88 | oz/yd ² | D-5848 |
| Primary Backing Weight | 6 | oz/yd ² | D-5848 |
| Secondary Coating Weight | 22 | oz/yd ² | D-5848 |
| Tuft Bind | > 8 | lbs. | D-1335 |
| Grab Tear Strength (Average) | > 200 | lbs. | D-5034 |
| Total Yarn Linear Density | 12,000 | Denier | D-1577 |
| Elongation to Break | > 30 | % | D-2256 |
| Yarn Breaking Strength | > 20 | lbs. | D-5793 |
| Machine Gauge | 3/8 | inches | D-5793 |
| Flammability | Passed | - | D-2859 |
| Water Permeability | > 250 | in/hr | D-1551 |
| Fabric Width | 15 | ft | - |